

OPTIMIZATION OF INJECTION MOLDING PARAMETERS IN MOLD SM20 USING THE TAGUCHI-GREY RELATIONAL ANALYSIS (GRA) METHOD FOR REDUCING SHORT-SHOT DEFECTS AND CYCLE TIME

Abraham Thiong Ajak Thiong¹, Mochamad Muzaki²

State Polytechnic of Malang^{1,2}

Thiongajak2000@gmail.com

Received : 28 July 2025, Revised: 29 July 2025, Accepted : 31 July 2025

*Corresponding Author

ABSTRACT

Injection molding has become a favorite technique of manufacturing high quality of specific plastic components. Nevertheless, typical flaws like short-shot flaws and long cycle times may jeopardize the quality of a product and decrease the productivity. This project is aimed at the optimization of three major process parameters; that is, the nozzle temperature, injection pressure, and injection time, which will be the three set at four levels to achieve an improvement in the performance of Mold SM20. The Taguchi experimental design used is an L16 orthogonal array and this makes the experimental design to be successfully reducing the number of trial required. As part of dealing with the two-fold goals of QED reduction and cycle time, Grey Relational Analysis (GRA) would be used in multi-response optimization. Gra means normalization, calculating of grey relational coefficients and the calculation of grey relational grades (GRG). The outcomes show that injection pressure can play an important role in combined response, whereas nozzle temperature and injection time present a less important role. The best combination of parameters (temperature of the nozzle 225o C, injection pressure 55 bar and injection time 2.0 sec) gave the best value of GRG, 0.841278 which indicates better performance of the process, both quality-wise as well as efficiency-wise.

Keywords : *Injection molding; Taguchi method; Grey Relational Analysis (GRA); short-shot defects; cycle time*

1. Introduction

Due to being precise and having fast cycles and low costs, injection molding remains a heavy part of the mass-weight of all plastic parts produced worldwide with more than 30 percent (Selvaraj et al., 2022; Roslan et al., 2019). New technologies including the use of new tools and simulation technologies have increased moldability and defect prevention (Kim & Song, 2021; Huang et al., 2022)

They are not without difficulties, in general, the short-shot defects, warpage, and shrinkage are likely to occur, and they are frequently caused by the inadequate optimization of parameters, such as pressure, temperature, and injection time (Nguyen & Nguyen, 2023; Aribowo & Dani, 2023; Moayyedien et al., 2021). Such quality problems do not only degrade structural integrity but also lead to elevated scrap rates and break obligations in production functioning. Next, throughput with the cycle time optimization process important in sustainable manufacturing (Gokalp & Karadag, 2020), in which the cooling stage can take up to 80% of the entire process time (Goktas & Gunaldas, 2020; Iranmanesh et al., 2019)

The hybrid Taguchi-Grey Relational Analysis (GRA), is a suitable solution to these complex problems. Along with the effectiveness of the orthogonal design provided by Taguchi, multi-response optimization of the GRA customization, manufacturers can turn the competing quality requirement to a single unified performance grade (Tan et al., 2024; Annabila et al., 2023) Such combined technique has already been applied in application field as composite connector molding and sink-mark reduction in the area of improving the product and precision of process and lead to quality reliability.

The study is by use of Taguchi-GRA since it is in line with industry best practices and academic approval of this optimisation of the injection moulding parameters of nozzle temperature, injection pressure and injection time of Mold SM20. The objective is to reduce simultaneously short-shot defects and cycle time. In a well designed experimental scheme (L16 array) and a well developed grey relational analysis (normalisation, calculating coefficients, and calculating grade), this strategy will provide a set of parameters that will yield better products, and better manufacturing at a higher efficiency rate in a data-driven verified plot.

2. Literature Review

Mohamed (Mohamed et al. 2019) successfully demonstrated the integration of Taguchi and Grey Relational Analysis (GRA) methods to optimize injection molding parameters—namely melting temperature, injection pressure, injection speed, and cooling time—for improving the tensile strength and hardness of rice husk–polypropylene composites. Utilizing an L9 orthogonal array, they applied S/N ratio analysis and GRA to convert multiple quality responses into a single performance metric. The results indicated that injection pressure had the most significant effect, followed by melting temperature, injection speed, and cooling time.

Nor (Nor et al. 2011) reports a comprehensive study on optimizing injection molding parameters using the Taguchi method combined with Grey Relational Analysis (GRA). The research investigates six critical parameters—namely injection pressure, injection temperature, powder loading, mold temperature, holding pressure, and injection rate—each evaluated at three levels using an L27 orthogonal array. The study aims to improve multiple quality characteristics of the green part, including defect minimization, mechanical strength, and density. The GRA approach effectively consolidates these multiple responses into a single grade for ranking, enabling the identification of an optimal parameter setting: 450 bar injection pressure, 140 °C injection temperature, 65% powder loading, 50 °C mold temperature, 500 bar holding pressure, and 10 cm/s injection rate. ANOVA results reveal that injection temperature contributes the most significantly (26.37%) to overall quality, underscoring the importance of thermal control in the molding process.

Ali (Md Ali et al. 2018) investigates the application of the Taguchi-GRA hybrid method for optimizing multiple quality responses in the plastic injection molding process. The study focuses on four process parameters: mold temperature, melting temperature, injection time, and cooling time, aiming to optimize six quality responses—part weight, shrinkage, warpage, ultimate tensile strength, tensile modulus, and elongation percentage. Using a Taguchi orthogonal array (L9) and Autodesk Moldflow simulations, they conducted experiments and applied Grey Relational Analysis to determine the optimal combination of parameters. The findings show that the optimal setting (Run 4) significantly reduced warpage and shrinkage while maintaining strong mechanical properties and dimensional accuracy.

Jamaludin (Jamaludin et al. 2010) investigates the application of the hybrid Grey-Taguchi method to optimize injection molding parameters for producing high-quality green compacts from stainless steel powder. Six key parameters— injection pressure, injection temperature, powder loading, mold temperature, holding pressure, and injection speed—were analyzed at three levels using an L27 orthogonal array. The study successfully applied Grey Relational Analysis (GRA) to combine multiple quality objectives—appearance, strength, and density—into a single Grey Relational Grade (GRG) for optimization. The results identified mold temperature as the most significant factor, contributing 38.82% to performance improvement. The optimal parameter combination (A1 B1 C0 D0 E2 F1) yielded high GRG values in confirmation trials, validating the method's effectiveness.

The study by Mahajan (Mahajan and Ulhe 2020) investigates the optimization of injection molding process parameters to minimize short-shot defects using the Taguchi Method and

ANOVA. Conducted on CPVC specimens molded into $\frac{3}{4}$ inch elbow fittings, the research examines four controllable parameters: injection pressure, mold closing speed, mold pressure, and screw speed, each at three levels arranged in an L9 orthogonal array. The quality characteristic used is part weight, with the "larger-the-better" signal-to-noise (S/N) ratio indicating defect minimization. The findings reveal that mold closing speed is the most influential parameter in reducing short-shot defects, followed by screw speed, while injection pressure and mold pressure have lesser effects. ANOVA confirms the significance of mold closing speed, contributing over 70% to the performance improvement. This research supports the importance of robust design methodologies like Taguchi in identifying critical parameters for quality optimization.

3. Research Methods

3.1 Research Design

This applied quantitative experimental research was conducted at PT Betts Indonesia from February to July 2025. The goal was to identify the optimal injection molding parameters using Taguchi and GRA methods.

3.2 Equipment and Materials

- a. Machine: Nissei injection molding machine used in this study to features a multi-cavity system with adjustable settings for injection pressure, time, and nozzle operation, suitable for high-volume, precision production.



Figure 1 Injection Molding Machine Nissei

Mold: SM20, 24-cavity Figure 2 shows the SM20 mold cavity, a multi-cavity mold used in this study to produce multiple plastic parts simultaneously within a single injection cycle.



Figure 2 Mold SM20 cavity

Material: HDPE (6070EA) HDPE was chosen for its strength, durability, and suitability for injection molding. Its stable behavior under heat and pressure makes it ideal for analyzing defects like short-shot. Figure 3.6 shows the HDPE pellets used in the trials.



Figure 3 High-Density Polyethylene (HDPE)

Controlled parameters: Injection speed (65%), back pressure (190%), cooling time (6 s), holding pressure (80 MPa), holding time (10 s)

3.3 Variables and Levels

Table 1 Research factors and their respective levels

Factors	Level 1	Level 2	Level 3	Level 4
Nozzle Temperature	215°C	220°C	225°C	230°C
Injection Pressure	55 bars,	50 bars,	45 bars,	40 bars,
Injection Time	4s	3.5s	2.5s	2s

Responses:

- A. Short-shot defect (defective units per mold)
- B. Cycle Time (seconds)

3.4 Experimental Procedure

The experiment followed an L16 orthogonal array design to study the effects of the three factors. Short-shot defects were calculated as the percentage of defective parts in one mold cycle. Cycle time was recorded from the machine display.

Table 2 Data form experiment

Run	Nozzle Temp. [°C]	Inject. Press. [Bar]	Inject. Time [sec.]	Cycle time [sec.]				Short-shot [unit/mold]			
				1 st	2 nd	3 rd	4 th	1 st	2 nd	3 rd	4 th
1	215	55	4	20	20	20	20	0	0	0	0
2	215	50	3,5	19,5	19,5	19,5	19,5	0	0	0	0
3	215	45	2,5	18,5	18,5	18,5	18,5	23	22	17	15
4	215	40	2	18	18	18	18	24	24	24	24
5	220	55	3.5	19,5	19,5	19,5	19,5	0	0	0	0
6	220	50	4	20	20	20	20	0	0	0	0
7	220	45	2	18	18	18	18	24	23	23	23
8	220	40	2,5	18,5	18,5	18,5	18,5	24	24	24	22
9	225	55	2,5	18,5	18,5	18,5	18,5	0	0	0	0
10	225	50	2	18	18	18	18	22	21	17	18
11	225	45	4	20	20	20	20	0	1	0	0
12	225	40	3,5	19,5	19,5	19,5	19,5	22	14	22	23
13	230	55	2	18	18	18	18	24	23	23	23
14	230	50	2,5	18,5	18,5	18,5	18,5	24	24	24	24
15	230	45	3,5	19,5	19,5	19,5	19,5	24	23	23	24
16	230	40	4	20	20	20	20	24	24	24	24

3.5 Grey Relational Analysis

To optimize both cycle time and short-shot defects, responses were converted into a single Grey Relational Grade (GRG). This involved normalization, delta calculation, Grey Relational Coefficient (GRC), and finally GRG. An example is shown using data from Run 1.

a. Normalization was applied using:

Nominal is best (short shot).

a. Normalization of short-shot

It is known:

Max short-shot data = 1

Min short-shot data = 0

Max data – Min data= 1

short-shot Run 1 = 0

So normalization of cycle time value is:

$$X'_i(k) = \frac{|MAX x_i(k) - x_i(k)|}{|MAX x_i(k) - MIN x_i(k)|}$$

$$X'_i(k) = \frac{|1 - 0|}{|1|}$$

$$X'_i(k) = 1$$

Smaller is better (cycle time)

It is known:

I. Max cycle-time data = 20 second

II. Min cycle-time data = 18 second

III. Max data - Min data = 2 second

IV. Cycle time Run 1 = 20 second

So normalization of cycle time value is:

$$X'_i(k) = \frac{|MAX x_i(k) - x_i(k)|}{|MAX x_i(k) - MIN x_i(k)|}$$

$$X'_i(k) = \frac{|20 - 20|}{|2|}$$

$$X'_i(k) = 0$$

Grey Relational Coefficient (GRC) and Grey Relational Grade (GRG) were calculated. The highest GRG indicated the optimal setting.

3.6 Statistical Hypothesis Testing

Two-way ANOVA was performed on GRG to evaluate the significance of each factor. A p-value < 0.05 was considered statistically significant.

4. Results and Discussions

4.1 Optimal Parameter Combination

The baseline data revealed that **Injection Pressure (55 bar)** and **moderate Nozzle Temperature (215°C)** contributed most to reducing short-shot defects, while **short Injection Time (2.0 s)** helped optimize cycle efficiency. These trends informed the selection of optimal parameter levels using the integrated Taguchi-GRA framework, ultimately resulting in a **GRG score of 0.822** in the best-performing trial.

4.2 ANOVA Analysis

ANOVA revealed that injection pressure significantly affected GRG ($p < 0.05$), indicating its dominant influence on combined short-shot and cycle time performance. Nozzle temperature and injection time showed no significant effect.

Source	DF	Seq SS	Adj SS	Adj MS	F	P
Nozzle Temp	3	0,08705	0,08705	0,029016	4,01	0,070
Injection Pressure	3	0,13454	0,13454	0,044848	6,20	0,029
Injection Time	3	0,03861	0,03861	0,012869	1,78	0,251
Residual Error	6	0,04337	0,04337	0,007229		
Total	15	0,30357				

S	R-Sq	R-Sq(adj)
0,0850	85,71%	64,28%

5. Conclusion

In the study of the optimisation of injection molding process parameters (nozzle temperature, injection pressure, and injection time) for short-shot defects and cycle time, several conclusions can be drawn as follows:

1) **Based on the statistical analyses, it can be concluded that:**

- Injection pressure is the most influential parameter, with a statistically significant impact on GRG.
- Nozzle temperature shows potential influence, though not statistically significant.
- Injection time has no significant effect, though shorter durations may offer performance benefits and warrant further investigation.
- The overall model is statistically sound and supports targeted optimization efforts focused on pressure settings to minimize defects and reduce cycle time

2) **The combination of factor levels that results in the highest average GRG**

(0,841278)—and thus the best overall process performance—is as follows:

- Nozzle Temperature: 225°C (Level 3)
- Injection Pressure: 55 bar (Level 4)
- Injection Time: 2.0 seconds (Level 1)

SUGGESTION

Further studies are needed to optimise the quality of injection molding products with different combinations from the current study.

References

- Abutu, Joseph et al. 2018. "Production and Characterization of Brake Pad Developed From Coconut Shell Reinforcement Material Using Central Composite Design." *Sn Applied Sciences*.
- Annabila, Muflikh Arizka, Indah Widiastuti, and Yuyun Estriyanto. 2023. "Optimizing the Injection Molding Parameters of Mask Waste Recycling Into Door Knob Products." *E3s Web of Conferences*.
- Aribowo, Muhammad Sambodo, and Agus Dani. 2023. "The Effect of Holding Pressure and Inject Pressure to Short Shot Defect in Injection Molding Cover Pot." *Logic Jurnal Rancang Bangun Dan Teknologi*.
- Baccouch, Zaineb et al. 2019. "Investigation on the Effects of Recycling and Injection Parameters on Gloss Properties of Smooth Polypropylene Parts."
- Banh, Quoc-Nguyen et al. 2025. "Optimization of Process Parameters for Sink Marks and Shrinkage Reduction in Family Molds Using Grey-Based Taguchi Method." *Advances in Mechanical Engineering*.
- Baum, Markus, Denis Anders, and Tamara Reinicke. 2023. "Approaches for Numerical Modeling and Simulation of the Filling Phase in Injection Molding: A Review." *Polymers*.
- Begić-Hajdarević, Đerzija et al. 2019. "Multi-Response Optimization of Laser Cutting Parameters Using Grey Relational Analysis."

- Bender, Theresa et al. 2023. "Benchmarking the Impact of Noise on Deep Learning-Based Classification of Atrial Fibrillation in 12-Lead ECG."
- Châabène, A, Sami Chatti, and Mouna Ben Slama. 2022. "Optimization of the Cooling of a Thermoplastic Injection Mold." *Annals of Dunarea De Jos University of Galati Fascicle Xii Welding Equipment and Technology*.
- Chen, Jianyu, Chunying Liu, and Ming-Shyan Huang. 2019. "Tie-Bar Elongation Based Filling-to-Packing Switchover Control and Prediction of Injection Molding Quality." *Polymers*.
- Chen, Joseph C, Gangjian Guo, and Stephen Jala. 2024. "Development of EDART Based Online Diameter Prediction Systems in Injection Molding With Multiple Linear Regression and Fuzzy Logic." *Engineering Research Express*.
- Chen, Yaowei et al. 2022. "Injection Molding and Shear-induced Stress Simulation of Poly (Styrene-ethylene-butylene-styrene) and Polypropylene Blends." *Journal of Applied Polymer Science*.
- Cheung, Wai Ming, Jun T Leong, and Parag Vichare. 2017. "Incorporating Lean Thinking and Life Cycle Assessment to Reduce Environmental Impacts of Plastic Injection Moulded Products." *Journal of Cleaner Production*.
- Dang, Zhehui. 2023. "Analysis of Factors Influencing Mountain Wind Power Generation Based on Grey Relational Analysis."
- Das, Argha, Arindam Majumder, and Pankaj Kr. Das. 2014. "Detection of Apposite PSO Parameters Using Taguchi Based Grey Relational Analysis: Optimization and Implementation Aspects on Manufacturing Related Problem." *Procedia Materials Science* 6(May 2015): 597–604. <http://dx.doi.org/10.1016/j.mspro.2014.07.074>.
- Davis, Rahul, and Pretesh John. 2018. "Application of Taguchi-Based Design of Experiments for Industrial Chemical Processes."
- Fernandes, Célio, António José Pontes, Júlio César Viana, and António Gaspar-Cunha. 2018. "Modeling and Optimization of the Injection-Molding Process: A Review." *Advances in Polymer Technology* 37(2): 429–49.
- Fontana, Roberto, and Fabio Rapallo. 2019. "Unions of Orthogonal Arrays and Their Aberrations via Hilbert Bases."
- Formas, Krzysztof et al. 2022. "Injection Molding Process Simulation of Polycaprolactone Sticks for Further 3D Printing of Medical Implants." *Materials*.
- Ghaithan, Ahmed M, Mohammed Arshad Khan, Awsan Mohammed, and Laith A Hadidi. 2021. "Impact of Industry 4.0 and Lean Manufacturing on the Sustainability Performance of Plastic and Petrochemical Organizations in Saudi Arabia." *Sustainability*.
- Gnanavelbabu, A et al. 2020. "Turning Process Characteristics of Aluminium Matrix Hybrid Composite Using Grey Relational Surface Methodology."
- Gnatowski, A et al. 2022. "Computer Simulations of Injection Process of Elements Used in Electromechanical Devices." *Materials*.
- Göktaş, Mustafa, and Abdulmecit Gültaş. 2020. "Production of Plastic Injection Molds With Conformal Cooling Channels by Laminated Brazing Method." *Gazi University Journal of Science*.
- Hamzaçebi, Coşkun. 2021. "Taguchi Method as a Robust Design Tool."
- Hartono, Moh., Gumono, Hangga Wicaksono, and Ramadhan Araya Ismoyo. 2022. "Characterization of Differences in Cavity Positions Orientation in the Multi Cavity Plastic Molding Process on the Product Defects."
- Hentati, Fatma, and Neila Masmoudi. 2021. "Influence of Injection Molding Parameters on the Mechanical Properties of Injected PC/ABS Parts."
- Hirai, Takayuki et al. 2019. "High-temperature Crystallization of Immiscible Polymer Blends Induced by the Shear Flow in Injection Molding." *Polymer Crystallization*.
- Hong, Tengjiao et al. 2025. "Multi-Objective Optimization of Injection Molding Process Parameters for Junction Boxes Based on BP Neural Network and NSGA-II Algorithm." *Materials*.
- Huang, Haowei et al. 2020. "Two-Dimensional Nanomaterials for Anticorrosive Polymeric Coatings: A Review." *Industrial & Engineering Chemistry Research*.
- Huang, Huei-Yu et al. 2022. "Optimal Processing Parameters of Transmission Parts of a Flapping-Wing Micro-Aerial Vehicle Using Precision Injection Molding." *Polymers*.

- Huang, Ming-Shyan, Shih-Chih Nian, and Guan-Ting Lin. 2021. "Influence of v/P Switchover Point, Injection Speed, and Holding Pressure on Quality Consistency of Injection-molded Parts." *Journal of Applied Polymer Science*.
- Iranmanesh, Mohammad et al. 2019. "Impact of Lean Manufacturing Practices on Firms' Sustainable Performance: Lean Culture as a Moderator." *Sustainability*.
- Jamaludin, Khairur Rijal et al. 2010. "Application of the Grey-Taguchi Method to the Optimization of Metal Injection Molding (MIM) Process." *Key Engineering Materials* 443: 63–68.
- Jha, Neeraj Kumar, G Bharath Reddy, and V.Vijendra kumar. 2021. "Design and Process Analysis of Single Cavity Injection Molding Die for Plastic Wing Nut." *CVR Journal of Science & Technology*.
- Kalhapure, Vaibhav A, and Hrishikesh P Khairnar. 2021. "Taguchi Optimization for Wear Behaviour of Drum Brake Shoe Interface."
- Kannan, Vimalathithan Paramsamy et al. 2019. "Thermal Degradation Kinetics of Polypropylene/Clay Nanocomposites Prepared by Injection Molding Compounder." *Polymer Composites*.
- Kim, Dah Hee, and Young Seok Song. 2021. "Moldability Improvement in Microinjection Molding via Film Lamination." *Polymers and Polymer Composites*.
- de Kort, Gijs W et al. 2020. "Importance of Viscosity Control for Recyclable Reinforced Thermoplastic Composites." *Macromolecules*.
- Kuo, Chil-Chyuan et al. 2024. "Enhancing the Cooling Efficiency of Aluminum-Filled Epoxy Resin Rapid Tool by Changing Inner Surface Roughness of Cooling Channels." *Polymers*.
- Kuo, Chil-Chyuan, Trong-Duc Nguyen, Yijun Zhu, and Shixun Lin. 2021. "Rapid Development of an Injection Mold With High Cooling Performance Using Molding Simulation and Rapid Tooling Technology." *Micromachines*.
- Kuo, Chil-Chyuan, and Shao-Xuan Qiu. 2021. "A Simple Method of Reducing Coolant Leakage for Direct Metal Printed Injection Mold With Conformal Cooling Channels Using General Process Parameters and Heat Treatment." *Materials*.
- L.D.Mahajan, and P.N.Ulhe. 2020. "Analysis of Injection Molding Process To Reduced Defects (Short-Shot)." *International Journal of Engineering Technologies and Management Research* 5(6): 113–19. <http://dx.doi.org/10.29121/ijetmr.v5.i6.2018.251>.
- La, Moonwoo, Jea Gu Lee, and Sung Jea Park. 2017. "Numerical and Experimental Investigation of Plastic Injection Molding of Micro-engineered Surfaces." *Polymer Engineering & Science*.
- Lee, Yongsun, Jinrae Cho, and Seong-Ryeol Han. 2022. "Optimization of Injection Molding of Automotive Plastic Horn Cover Part Using Taguchi Method and Reverse Engineering." *Materiale Plastica*.
- Lei, Xue et al. 2024. "Improving the Electrical Conductivity of Multiwalled Carbon Nanotubes-containing Micromoldings via in Situ Construction of Electrically Conductive Networks." *Polymer Composites*.
- Li, Jiquan et al. 2024. "Study on the Processes and Warpage of <sc>double-injection-molded</Scp> Parts Containing <sc>PP</Scp> Recycled Materials." *Polymer Engineering & Science*.
- Li, Xiaoyan et al. 2020. "Effect of Injection Molding on Structure and Properties of Poly(Styrene-ethylene-butylene-styrene) and Its Nanocomposite With Functionalized Montmorillonite." *Journal of Applied Polymer Science*.
- Liao, Qianghua et al. 2019. "Efficient and Precise Micro-Injection Molding of Micro-Structured Polymer Parts Using Micro-Machined Mold Core by WEDM." *Polymers*.
- Lin, Chao-Ming, and Yun-Ju Chen. 2021. "Taguchi Optimization of Roundness and Concentricity of a Plastic Injection Molded Barrel of a Telecentric Lens." *Polymers*.
- Lin, Chao-Ming, and Ting-Hsuan Miao. 2022. "Optimization of Injection-Compression Molding Processing Conditions for Fresnel Lens Based on Optical Performance and Geometry Deformation Considerations." *Ieee Access*.
- Lin, Chao-Ming, Jih-Jyun Wu, and Chung-Ming Tan. 2020. "Processing Optimization for Metal Injection Molding of Orthodontic Braces Considering Powder Concentration Distribution of Feedstock." *Polymers*.

- Liu, Jingru, Xinxu Zhu, and Zheng Cao. 2019. "Poly(Acrylonitrile–Butadiene–Styrene) as a Special B-Nucleating Agent on the Toughness of Isotactic Polypropylene." *Polymers*.
- Liu, Jitao, Shuxiang Zhang, Guoqun Zhao, and Guilong Wang. 2017. "Numerical and Experimental Investigations on Polymer Melt Flow Phenomenon in a Vario-thermal Mold Cavity." *Journal of Applied Polymer Science*.
- M Adzhar, M S, M N Harun, and Amir Putra Md Saad. 2023. "Cooling Channel Selection for Big Rectangular Plastic Parts in Injection Molding." *Iop Conference Series Materials Science and Engineering*.
- Ma, Yitao et al. 2023. "Study on the Evaluation and Compensating Strategy for the Wear Damage of Non-return Valve During Injection Molding Process." *Polymer Engineering & Science*.
- Masato, Davide et al. 2018. "Comparison of Crystallization Characteristics and Mechanical Properties of Polypropylene Processed by Ultrasound and Conventional Micro-Injection Molding." *The International Journal of Advanced Manufacturing Technology*.
- Mbarek, Souad et al. 2020. "Impact of Injection Parameters on Gloss Properties of Grained Polypropylene Parts."
- Md Ali, M. A. et al. 2018. "Multi-Response Optimization of Plastic Injection Moulding Process Using Grey Relational Analysis Based in Taguchi Method." *Journal of Advanced Manufacturing Technology* 12(Specialissue3): 87–98.
- Mei, Yi, and Maoyuan Xue. 2022. "Optimization of Injection Molding Process Parameters Based on GA-ELM-GA." *Matec Web of Conferences*.
- Mendible, Gabriel Antonio, Jack A Rulander, and Stephen Johnston. 2017. "Comparative Study of Rapid and Conventional Tooling for Plastics Injection Molding." *Rapid Prototyping Journal*.
- Mensler, Holger, Shujun Zhang, and Thomas Win. 2019. "A Method for Determining the Flow Front Velocity of a Plastic Melt in an Injection Molding Process." *Polymer Engineering & Science*.
- Moayyedian, Mehdi, Ali Dinç, and Ali Mamedov. 2021. "Optimization of Injection-Molding Process for Thin-Walled Polypropylene Part Using Artificial Neural Network and Taguchi Techniques." *Polymers*.
- Mohamed, Sity Ainy Nor et al. 2019. "Integration of Taguchi-Grey Relational Analysis Technique in Parameter Process Optimization for Rice Husk Composite." *BioResources* 14(1): 1110–26.
- Monti, Marco et al. 2021. "Dielectric Spectroscopy of PP/MWCNT Nanocomposites: Relationship With Crystalline Structure and Injection Molding Condition." *Nanomaterials*.
- Morales Méndez, Jonathan David, and Ramón Silva-Rodríguez. 2018. "Environmental Assessment of Ozone Layer Depletion Due to the Manufacture of Plastic Bags." *Heliyon*.
- Muthu, P. 2023. "Optimization of Dry Sliding Wear Behaviour of Industrial Wastes Reinforced Aluminium Based Metal Matrix Composites." *Materialwissenschaft Und Werkstofftechnik*.
- N. Vieira, Alexandre L, R.D.S.G. Campilho, F J G Silva, and Luís Pinto Ferreira. 2021. "Increasing the Environmental Sustainability of an Over-Injection Line for the Automotive Component Industry." *Sustainability*.
- Nguyen, Huu-That, and Minh-Quan Nguyen. 2023. "A Numerical Simulation and Multi-Objective Optimization for the Plastic Injection Molding of a Centrifugal Pump Casing." *Iop Conference Series Earth and Environmental Science*.
- Nguyen, Tran-Phu, Thanh Long Le, and Tran Minh The Uyen. 2022. "Numerical Simulation on the Effect of the Cooling Channel Design on the Warpage of a Thin-Wall Injection Molding Product." *Materials Science Forum*.
- Nguyen, Truong Giang, Pham Son Minh, and Anh Son Tran. 2020. "Verifying the Gas Heating Method for Injection Molding." *Key Engineering Materials*.
- Nor, N.H. Mohamad et al. 2011. "Injection Molding Parameter Optimization of Titanium Alloy Powder Mix with Palm Stearin and Polyethylene for Multiple Performance Using Gray Relational Analysis." 10(11): 1833–38.
- Ogorodnyk, Olga et al. 2018. "Application of Machine Learning Methods for Prediction of Parts Quality in Thermoplastics Injection Molding."
- Ogorodnyk, Olga, Ole Vidar Lyngstad, Mats Larsen, and Kristian Martinsen. 2020. "Prediction of Width and Thickness of Injection Molded Parts Using Machine Learning Methods."

- Oktariani, Erfina, and Rita Istikowati. 2017. "Multi Responses Optimization of Decarboxylation Process of Free Fatty Acid (FFA) Into Biodiesel Using Grey Relational Analysis (GRA)." *Matec Web of Conferences*.
- Pacella, Massimo, Matteo Mangini, and Gabriele Papadia. 2023. "Utilizing Mixture Regression Models for Clustering Time-Series Energy Consumption of a Plastic Injection Molding Process." *Algorithms*.
- Pacheco, A B et al. 2023. "Polymeric Materials Obtained by Extrusion and Injection Molding From Lignocellulosic Agroindustrial Biomass." *Polymers*.
- Park, Hong-Seok, and Xuan-Phuong Dang. 2018. "Technology for Improving Productivity and Quality of Injection Molding."
- Poszwa, Przemysław, and Marek Szostak. 2018. "Influence of Scale Deposition on Maintenance of Injection Molds." *Eksploatacja I Niezawodnosc - Maintenance and Reliability*.
- Prasetyo, Angger Bagus, and Fauzun Fauzun. 2018. "Numerical Study of Effect of Cooling Channel Configuration and Size on the Product Cooling Effectiveness in the Plastic Injection Molding." *Matec Web of Conferences*.
- Rabbi, M S, Tansirul Islam, and G M Sadiqul Islam. 2021. "Injection-Molded Natural Fiber-Reinforced Polymer Composites—a Review." *International Journal of Mechanical and Materials Engineering*.
- Rachman, Farizi, Bayu Wiro Karuniawan, Ika Pramestiani, and Noorman Rinanto. 2023. "Optimizing Injection Molding Parameters to Cycle Time of Bioring Cone Cup Products With Taguchi Method." *International Journal of Marine Engineering Innovation and Research*.
- Ri, Ryong Hui, and Won-Chol Yang. 2024. "Optimization of the Metal Injection Molding Process With 316L Stainless Steel Powder and Influence Analysis of Process Parameters Using the Taguchi-Madm-Based Hybrid Method." *Acs Omega*.
- Roslan, Norshahira et al. 2019. "Optimization of Shrinkage and Strength of the Molded Part Produced Using LDPE (Virgin and Recycled) Material: A Review." *Iop Conference Series Materials Science and Engineering*.
- Sahoo, Sarat Kumar et al. 2019. "Analysis and Optimization of Wire EDM Process of Titanium by Using GRA Methodology." *Materials Science Forum*.
- Selvaraj, Senthil Kumaran et al. 2022. "A Review on Machine Learning Models in Injection Molding Machines." *Advances in Materials Science and Engineering*.
- Sorgato, Marco, Davide Masato, and Giovanni Lucchetta. 2017. "Effects of Machined Cavity Texture on Ejection Force in Micro Injection Molding." *Precision Engineering* 50(February 2018): 440–48.
- Struchtrup, Alexander Schulze, Dimitri Kvaktun, and Reinhard Schiffers. 2020. "A Holistic Approach to Part Quality Prediction in Injection Molding Based on Machine Learning."
- Sulung Wibawansyah, Sulung Wibawansyah. 2024. "Identify Product Defects in the Injection Molding Process." *Procedia of Engineering and Life Science*.
- Surace, Rossella et al. 2021. "Micro Injection Molding of Thin Cavities Using Stereolithography for Mold Fabrication." *Polymers* 13(11).
- Talbi, Mourad, Riadh Baazaoui, and Med Salim Bouhleb. 2021. "Speech Enhancement Based on LWT and Artificial Neural Network and Using MMSE Estimate of Spectral Amplitude."
- Tan, Mingbo, Size Peng, Y Z Huo, and Maojun Li. 2024. "Multi-Objective Optimization of Injection Molding Parameters for Manufacturing Thin-Walled Composite Connector Terminals." *Materials*.
- Teich, Sebastian, Edmund Haberstroh, and Ulrich Giese. 2021. "Experimental and Simulative Investigation of a Multistage <sc>2K</sc> Injection Molding Process of <sc>PA6</sc> and <sc>EPDM</sc>." *Journal of Applied Polymer Science*.
- Tlegenov, Olzhas et al. 2025. "Rapid Quantitative Assessment of Residual Stress States in <sc>PLA</sc> Components Enabled by the Combination of Photoelasticity and the Hole Drilling Method." *Biopolymers*.
- Tran, Ngoc Tu et al. 2023. "Flow Disturbance Characterization of Highly Filled Thermoset Injection Molding Compounds Behind an Obstacle and in a Spiral Flow Part." *Polymers*.
- Trinh, Van-Long. 2024. "Application of Digital Simulation Tool in Designing of Injection Mold for Sustainable Manufacturing." *Eureka Physics and Engineering*.

- Wadhwa, Amandeep Singh, and Amit Chauhan. 2023. "Fabrication and Multi- Performance Optimization of Mechanical Properties of Novel Babbitt-Ilmenite Metal Matrix Composite Using Entropy Based Hybrid Taguchi-Grey Relational Analysis." *Engineering Research Express*.
- Wang, Minwen, Fatahul Arifin, and Van-Hanh Vu. 2019. "The Study of Optimal Molding of a LED Lens With Grey Relational Analysis and Molding Simulation." *Periodica Polytechnica Mechanical Engineering*.
- Wang, Yuandi, and Chang-Myung Lee. 2023. "Design and Optimization of Conformal Cooling Channels for Increasing Cooling Efficiency in Injection Molding." *Applied Sciences*.
- Wibowo, Ari et al. 2023. "Optimization of Plastic Injection Molding Process Parameters for Cowl B (L/R) Sink Mark Defects by Using Taguchi Methods and ANOVA." *Operations Excellence Journal of Applied Industrial Engineering*.
- Wu, Hu, Youmin Wang, and Mingyue Fang. 2021. "Study on Injection Molding Process Simulation and Process Parameter Optimization of Automobile Instrument Light Guiding Support." *Advances in Materials Science and Engineering*.
- Xie, Yuming et al. 2022. "Heteroatom Modification Enhances Corrosion Durability in High-Mechanical-Performance Graphene-Reinforced Aluminum Matrix Composites." *Advanced Science*.
- Xu, Yuxuan et al. 2021. "A Novel Strategy to Determine the Optimal Clamping Force Based on the Clamping Force Change During Injection Molding." *Polymer Engineering & Science*.
- Ying, Jiru et al. 2017. "Morphology and Rheology of PP/POE Blends in High Shear Stress Field." *Journal of Thermoplastic Composite Materials*.
- Zaccone, Marta et al. 2020. "Effect of Injection Molding Conditions on Crystalline Structure and Electrical Resistivity of PP/MWCNT Nanocomposites." *Polymers*.
- Zhang, Xiang et al. 2019. "Deep Neural Network Hyperparameter Optimization With Orthogonal Array Tuning."
- Zhao, Feng et al. 2024. "Plant Fiber-reinforced Composites Based on Injection Molding Process: Manufacturing, Service Life, and Remanufacturing." *Polymer Composites*.
- Zhao, Nanyang, Jiaoyuan Lian, Pengfei Wang, and Zhongbin Xu. 2022. "Recent Progress in Minimizing the Warpage and Shrinkage Deformations by the Optimization of Process Parameters in Plastic Injection Molding: A Review." *The International Journal of Advanced Manufacturing Technology*.
- Zhao, Runtian et al. 2025. "Effect of Injection Molding Parameters on the Tensile Strength of Short-Carbon-Fiber-Reinforced Nylon 6." *Polymers*.
- Zhao, Xintong et al. 2021. "Formation and Distribution of the Mesophase in Ultrasonic Micro-Injection-Molded Isotactic Polypropylene." *Macromolecules*.
- Zhou, Zhe-Wei et al. 2023. "Prediction of Short-Shot Defects in Injection Molding by Transfer Learning." *Applied Sciences*.
- Zhu, Junjie, Zhiwen Qiu, Yizhi Huang, and Wenhan Huang. 2021. "Overview of Injection Molding Process Optimization Technology." *Journal of Physics Conference Series*.
- Zimmermann, Philipp, and Volker Reichert. 2019. "Flexible Hot Runner Adapter Plates for Injection Molding Machines and Their Potential for Polymer Development." *Macromolecular Symposia*.
- [8] Ronal Watrionthos and Y. Yuhefizar, "Exploring Research Trends and Impact: A Bibliometric Analysis of RESTI Journal from 2018 to 2022," *Jurnal RESTI (Rekayasa Sistem dan Teknologi Informasi)*, vol. 7, no. 4, pp. 970–981, Aug. 2023, doi: 10.29207/resti.v7i4.5101.
- [9] IEEE, "IEEE Editorial Style Manual for Authors," *IEEE Editorial*, 2019.
- [10] O. Tur, A. Tur, V. Shabunina, and E. Chernaia, "The IEEE Style: Peculiarities of the Format and Application Prospects," in *2020 IEEE Problems of Automated Electrodrive. Theory and Practice (PAEP)*, IEEE, Sep. 2020, pp. 1–4. doi: 10.1109/PAEP49887.2020.9240790.
- [11] D. J. S. Montagnes, E. I. Montagnes, and Z. Yang, "Finding your scientific story by writing backwards," *Mar Life Sci Technol*, vol. 4, no. 1, pp. 1–9, Feb. 2022, doi: 10.1007/s42995-021-00120-z.
- [12] D. R. Hess, "How to Write an Effective Discussion," *Respir Care*, vol. 68, no. 12, pp. 1771–1774, Dec. 2023, doi: 10.4187/respcare.11435.